

NyoGel® 760G is the universal standard for dielectric grease specified by leading OEMs across many industries. These service bulletins are examples of where NyoGel® 760G has been listed as the recommended maintenance solution for components experiencing issues related to fretting corrosion, water intrusion, and/or oxidation.



BAE Systems

HybriDrive®
System Manual [401393-397](#)

General Motors

Brake Lights and Powertrain, Braking,
and Suspension Control Modules
Service Bulletin [09-06-03-004A-D](#)

C. E. Niehoff & Co.

C510 Alternator
Field Service Tip [SB0016A](#)

Harley Davidson

Diagnostic Trouble Codes P2135 and P2101
Technical Document [TT418](#)

Caterpillar Inc.

Fuel Injectors
Service Bulletin [03-40-001](#)

Hyundai

Control Wiring Harness
Service Bulletin [03-40-001](#)

Sensors Connections
Service Bulletin [SB02006](#)

Eaton, Dana, Roadranger

Input Shaft Sensor for Hybrid Transmissions
Service Bulletin [TAIB0847](#)

Lightning 18-way ECU Connector
Service Bulletin [TMIB-0156](#)

MACK

Engine Power Distribution Module (EPDM) Terminal Corrosion
Service Bulletin [SB725003](#)

Emerson Climate Technologies

Copeland Discus™ Compressors
Service Bulletin [AE8-1368 R2](#)

Molex

Lubrication of Mini-Fit SR. Tin Plated Terminals
Service Bulletin [AS-42815-001](#)

AC Bus Operation and Maintenance Manual
0000001425 3915018R2

Operation and Maintenance Manual
0000001581 2645901R5

ProStar+ Operation Manual
0000001301 3933971R5

TYPICAL PROPERTIES

Base Oil Properties	Conditions	NyoGel® 760G	Test Method
Chemistry		Silica / PAO	
Temperature Range		-40 to 135 °C	
Kinematic Viscosity	40 °C	400 cSt	ASTM D445
Viscosity Index		147.5	ASTM D2270
Grease Properties			
NLGI Grade		2	
Oil Separation	24 h, 100 °C	1.5%	ASTM D6184
Evaporation	24 h, 100 °C	0.3%	NYE CTM
Water Washout	1 h, 80 °C	2%	ASTM D1264
Copper Corrosion	24 h, 150 °C	1a, Slight Tarnish	ASTM D4048
Salt Spray Resistance	750 h	No Corrosion	ASTM B117-18
Dielectric Breakdown Voltage		11.2 kV	CTM*

*CTM: Nye Company Test Method

Nye Lubricants, Inc.

12 Howland Road
Fairhaven, MA 02719 USA
Ph: +1.508.996.6721
Email: contact@nyelubricants.com



NyeLubricants.com

